

WATERPROOFING



Vetoproof S

Elastomeric crack-bridging
cementitious waterproof membrane

Uses

- Waterproof lining for swimming pools (under tiling), water tanks, canals,...etc.
- Wet-areas waterproofing while receiving Saveto tile adhesives.
- Protecting concrete and masonry structures against ingress of chloride ions and carbonation.
- Negative hydrostatic pressure resistance.

Product Description

Vetoproof S is a two-component flexible polymer modified cementitious waterproof coating. It has unique crack bridging characteristics even after long-term water immersion. The product is suitable for use in contact with potable water and can withstand negative hydrostatic pressure.

Advantages

- Non-Toxic - approved in contact with drinking water.
- Flexible, crack bridging material.
- Ready to receive Saveto tile adhesives.
- Withstands hydrostatic pressures.
- Easy application by brush or roller.
- Bonds to green or damp concrete.
- Effective barrier to sulfates and chlorides.
- Excellent bond to concrete and masonry.

Technical Data

Vetoproof S	Typical Values @ 20°C
Pot Life (min)	45 - 60
Density (kg/Ltr approx)	1.7
Toxicity - BS6920	Pass
Chloride content	Nil
Resistance to positive water pressure DIN1048 (Bar)	> 8
Resistance to negative water pressure DIN1048 (Bar)	> 3
Chloride Diffusion	No penetration after 24 months
Application and cure temperature (°C)	5 to + 35

Standards Compliance

- EN 1992-3:2006 - Eurocode 2. Design of concrete structures. Liquid retaining and containing structures
- EN BS6920 - Elevated temperatures.
- EN 1504-2 (Surface protection systems for concrete)

Usage Instructions

Surface Preparation

All surfaces should be dry and free from contamination, such as oil, grease, loose particles, decayed matter, moss, algal growth, laitance, and all traces of mold release oils and curing compounds. This is best achieved by lightly grit-blasting the surface. Where moss, algae, or similar growths have occurred, please treat it with a proprietary biocide after the grit-blasting process. Remove spalled and deeply disintegrated concrete to sound concrete and repair it with a Saveto Repair System. Stop any running water with a suitable plugging mortar such as Vetoproof CR747. For further advice, consult the local Saveto office.

Pre-wetting of the substrate

Thoroughly dampen the substrate surface with water using a brush, roller, or spray bottle. High porosity substrates will require more dampening than dense substrates. Do not apply the coating when the substrate is wet, but allow the water to soak until the substrate is just visibly damp before proceeding. Remove any excess water by using a sponge.

Mixing

Shack Vetoproof S liquid concentrate and completely pour it from the plastic container into a suitably sized mixing container. Commence mixing with a propeller agitator attached to a slow speed drill (300-500 rpm). Add the powder component gradually to the liquid to avoid lump formation and mix for 2-4 minutes. Immediately use Vetoproof S after mixing to avoid settlement of sand. Part mixing is not allowed. Mix the whole kit. Do not mix more material than can be used within the pot life. Keep mixing Vetoproof S during the application.

Brush application

The most suitable brush is a soft-bristled wallpaper paste brush (220mm wide and 50mm deep). Where larger areas are to be applied, it is advisable to use a brush with a handle. Load the brush up well and spread the material to the required thickness. If the brush begins to drag during the application, do not add water to the material but dampen the surface again. Finish in one direction for a neat appearance.

Roller application

Application by roller has the benefit of quick speed over brush application, particularly on smooth substrates. A good quality medium hair roller is recommended. Load the roller well for ease of application. A heavy roller will leave a pattern on the substrate; therefore, it is important to use a finishing tool to produce a smooth coating with a uniform 0.75mm wet film thickness.

Legal Disclaimer

Saveto endeavors to ensure that any advice, recommendations, information it may give is accurate and correct. It cannot accept any liability either directly or indirectly arising from the use of its products because it has no direct or continuous control over where or how its products are applied, whether or not following any advice, specification, recommendation, or information given by us. Saveto has the right to change any of the technical datasheets specifications upon its discretion without prior notification.

Hard copies of TDSs are printed once or twice a year. Our technical data sheets are continuously updated as per R&D improvements and new 3rd party testing; kindly refer to our website for the latest updated TDSs.

Curing

Allow Vetoproof S to cure for at least 7 days before commissioning. At higher temperatures, 30°C cure for 4 days. At lower temperatures, below 12°C, cure the material for 10 days.

Cleaning

Immediately following the application, clean all tools and equipment with clean water. Hardened material can be removed by mechanical means.

Packaging & Coverage

Product	Pack Size	Coverage
Vetoproof S	20 kg Kit	1.7 kg/m ² / Coat @1 mm thickness

Stated consumption data are for general guidance. Actual consumption depends on the nature of the substrate, consistency used, method of application, and wastage.

Shelf Life & Storage

The original sealed bag and container of Vetoproof S have a shelf life of 12 months, provided it is stored clear of the ground in a dry, shaded place below 35°C.

Limitations

- Do not apply the product at a temperature less than +5°C.
- It is recommended to use fiberglass mesh in areas with either small cracks or in regions under particular stress while the first coat is still wet.
- For further information contact our technical department.

Health & Safety

Vetoproof S powder is irritating to the eyes, respiratory system, and skin. Avoid inhalation of dust and wear suitable respiratory protective equipment.

Vetoproof S liquid is not classified as dangerous. Vetoproof S, when mixed, becomes highly alkaline. Wear suitable protective clothing, gloves, and eye protection. For both components and the material, when mixed, avoid contact with eyes or skin. Rinse immediately with plenty of water and seek medical advice.

Vetoproof S is non-flammable.

For further information, please refer to the Product Material Safety Data Sheet.