



Vetoset CA549

Professional multipurpose grade adhesive to work with large tile format & multiple types of tiles (C2T S1)

Uses

- Ceramic tiles, porcelain tiles, natural stone conglomerates (granite & marble, terrazo), artificial Stone, and large format tiles.
- Laying of large format heavy tiles in internal and external applications.
- Tile over tile applications & with heated screeds.
- Laying on flexible substrates as well as dry walls (gypsum and cement boards).

Product Description

Vetoset CA549 is a cement based professional grade highly deformable tile adhesive that works with most types of tiles and flexible substrates. The product is composed of a blend of cement, carefully selected aggregates, special additives, and polymers that provide Vetoset CA549 with its unique properties. The product is suitable for internal as well as external use.

Advantages

- Easy to apply, a single component product.
- Highly deformable.
- Used internally and externally.
- High bond strength.
- Suitable for use with underfloor heating systems.
- Immersed and wet areas tiling.

Standards Compliance

- BS EN 12004:2010 as C2T S1
- SASO ISO13007-1as C2T S1

Technical Data

Vetoset CA549	Typical Values @ 25°C
Appearance	White or Grey Powder
Wet Density	Approx. 1.55 Kg/Liter
Application Thickness	2 to 6 mm
Pot Life	150 minutes
Adjustability	10 minutes
VOC	< 10 gm/Liter
SASO ISO 13007-1 Classification	C2T S1
Compressive Strength @ 28 day (BS EN 196-1)	10 MPa
Bond Strength @ 28 day (SASO ISO 13007-2)	≥ 1.0 MPa

Usage Instructions

Surface Preparation

The substrate should be sound, clean, free from loose material, grease, laitance, dirt, curing compound, or any other substance that might impair bond quality with the substrate.

Concrete, hollow blocks, and cement-based substrates must be sufficiently cured and irrigated by water 1hour before application. The surface should appear damp with no water pooling.

Gypsum boards, plasterboards, anhydrite screeds must be sufficiently dry and free from dust.

Mixing

For the preparation of mortar adhesive, pour into a container 5-6.6 liters of water for each 20kg bag of Vetoset CA549.

Add the powder to the water and mix for 3-4 minutes using a low- speed electric drill fitted with a suitable paddle until achieving a uniform, lump-free consistency. Allow the mixed material to stand for about 10 minutes and remix briefly without adding further water.

Application

Apply the mixed mortar adhesive in a thin layer, and firmly press it onto the surface that will be tiled and work with the trowel's flat edge. Comb the adhesive with a suitable notched trowel horizontally to achieve a 2 - 6 mm bed thickness. Spread the mortar adhesive to a manageable area that can be tiled within 5-10 minutes. Press the tiles firmly over the mortar adhesive and immediately knock them into the desired position. Adjust the position of the tiles, if required, within its adjustability time of 10 minutes after installation.

Use the back buttering method for large tile format (any tile with a breadth of more than 40cm) applications. Apply and comb the adhesive on the surface to be tiled. Also, add the adhesive to the backside of the tile with/without combing.

Allow the installed tiles to remain undisturbed for at least 24 hours.

Cleaning

Clean tools and equipment with water immediately after use. Remove the hardened material using mechanical means.

Legal Disclaimer

Saveto endeavors to ensure that any advice, recommendations, information it may give is accurate and correct. It cannot accept any liability either directly or indirectly arising from the use of its products because it has no direct or continuous control over where or how its products are applied, whether or not following any advice, specification, recommendation, or information given by us. Saveto has the right to change any of the technical datasheets specifications upon its discretion without prior notification.

Hard copies of TDSs are printed once or twice a year. Our technical data sheets are continuously updated as per R&D improvements and new 3rd party testing; kindly refer to our website for the latest updated TDSs.

Packaging & Coverage

Product	Pack Size	Coverage
Vetoset CA549	20 kg Bag	16 liters/ 20kg Bag

Stated consumption data are for general guidance. Actual consumption depends on the nature of substrate, method of application, and wastages.

Shelf Life & Storage

The original sealed bag of Vetoset CA549 has a shelf life of 12 months, provided it is stored clear of ground in a dry, shaded place below 35°C.

Health & Safety

Vetoset CA549 is highly alkaline; therefore, avoid direct contact with eyes or skin. It is recommended to use protective gloves and goggles during application. Any skin contact should be washed with soap and water. In case of eye irritation, immediately wash with a copious amount of clean cold water. Seek medical advice.

Vetoset CA549 is non-flammable.

For further information, please refer to the material safety data sheet.

Additional Information

Saveto manufactures a wide range of construction chemicals and speciality products for various applications.

For further information on these products and systems kindly check our website or contact your local Saveto representative.