



Masonry Grout Filler

Premixed cementitious masonry grout

Uses

- Apply Masonry Grout Filler on cement-based masonry blocks, masonry units, behind marble and cement panels, tiles or slabs, etc.
- Masonry Grout Filler is suitable for the application behind gypsum boards.

Product Description

Masonry Grout Filler is a ne grout category defined by American Concrete Institute (ACI), and is composed of portland cement, natural sand, selected ne aggregates, and special additives. The Masonry Grout Filler contains admixtures following ASTM C 476, C207, C260 to meet the ne grout category. Masonry Grout Filler is supplied as a dry powder in pre-weighed bags ready to use on-site, which requires only the addition of clean water to produce pourable grout. Masonry Grout Filler is ideal for grouting masonry blocks, masonry units, cores, and a filler behind marble slabs.

Advantages

- Factory controlled pre-blend ensures consistently high quality.
- Requires only the addition of water on-site at the time of usage.
- Suitable for ME harsh weather conditions.
- Easy application with uniform work flow enables high productivity & superior finishing.
- Strong adhesion.
- Good mechanical resistance.
- Excellent workability.

Technical Data

| Masonry Grout Filler | Typical Values @ 25°C |
|---|-----------------------|
| Appearance | Grey Powder |
| Aggregate size, max (mm) | 2.4 |
| Wet Density (kg/ltr) | 1.6 ± 0.1 |
| Bulk density (kg/ltr) | 1.55 approx. |
| Wet density (kg/ltr) | 1.85 approx. |
| Pot Life @25°C (Minutes) | 30-45 |
| Compressive strength @ 28 day (ASTM C109) (MPa) | > 14 |
| Flexural Strength @ 28 day (ASTM C348) (MPa) | > 5 |
| Yield (ltr/ton) | 570 approx. |
| Capillary Water Absorption EN 1015-18 | 14 |
| Slump (ASTM C143) (mm) | 260 |
| Slump Flow (ASTM C1611) (mm) | 680 |

Standards Compliance

- ASTM C476

The MSJC (Masonry Standard Joint Committee) considered the standard ASTM C476 in designing the mix, while ensuring following:

- Grout slump defines the fluidity and consistency of the mix (8"- 11").
- Grout compressive strength is related to the unit masonry strength f'm (must exceed f'm but must not less be than 2,000 psi).

Usage Instructions

Surface Preparation

The surface should be sound, clean free from loose materials, grease, laitance, dust, etc.

Mixing

For the preparation of masonry grout mixture, pour into a container 6.5 - 8 liters of water for each 50 Kg bag of Masonry Grout Filler.

Slowly add the powder to the water while mixing with an electric drill fitted with a suitable paddle for 2 minutes. Then continue mixing at medium-high speed for another 2-3 minutes until achieving a uniform, lump-free pourable consistency mix. The total mixing time is 4-5 minutes approx.

Please do not add water to the mix once it starts to stiffen.

Smooth Concrete Surfaces

Apply Spatter Dash SB prior to the application of Premix Plaster S.

Application

Pour the mixed material into the gap between masonry blocks, cement panels, or behind marble or gypsum board within the open time of 30-45 min.

Avoid air entrapment between the gaps while pouring the grout material.

For high lift grouting, the mixed material should be pumped or poured from a height to ensure the desired grout flow spread smoothly within the gaps.

We recommend using a mechanical grout pump for masonry grout placement as it will give more efficient filling and help in grout pumping in high rise structures.

Cleaning

Clean all tools immediately after finishing by water.

Clean hardened materials mechanically.

Legal Disclaimer

Saveto endeavors to ensure that any advice, recommendations, information it may give is accurate and correct. It cannot accept any liability either directly or indirectly arising from the use of its products because it has no direct or continuous control over where or how its products are applied, whether or not following any advice, specification, recommendation, or information given by us. Saveto has the right to change any of the technical datasheets specifications upon its discretion without prior notification.

Hard copies of TDSs are printed once or twice a year. Our technical data sheets are continuously updated as per R&D improvements and new 3rd party testing; kindly refer to our website for the latest updated TDSs.

Packaging & Coverage

| Product | Pack Size | Yield |
|----------------------|-----------|--------------------------------|
| Masonry Grout Filler | 50 kg Bag | 28.5 Lit wet/(50kg) bag powder |

Stated consumption data are for general guidance. Actual consumption depends on the nature of the substrate, method of application, and wastage.

Shelf Life & Storage

The original sealed bag of Masonry Grout Filler has a shelf life of 12 months, provided it is stored clear of ground in a dry, shaded place, at temperatures between 5°C - 35°C.

Health & Safety

Masonry Grout Filler is highly alkaline; therefore, avoid direct contact with eyes or skin. It is recommended to use protective gloves and goggles during application.

Any skin contact should be wash with soap & water. In case of eye irritation, immediately wash with a copious amount of clean cold water. Seek medical advice.

Masonry Grout Filler is non-flammable.

For further information, please refer to the material safety data sheet.

Additional Information

Saveto manufactures a wide range of construction chemicals and specialty products for various applications.

For further information on these products and systems kindly check our website or contact your local Saveto representative.