



# Vetoproof CM741

## Single component penetrating waterproofing system for concrete

### Uses

- On concrete and cementitious substrates.
- Swimming pools.
- Reservoirs and water tanks.
- Canals, harbors, and dams.
- Concrete pipes.
- Tunnels.
- Retaining walls.

### Product Description

VETOPROOF CM741 provides a total and permanent waterproofing solution to water leakage, ingress, or seepage in concrete structures or any cementitious substrates due to its unique, surface-applied penetrative capillary water proofing system. VETOPROOF CM741 works through internal crystallization that seals the pores and hairline cracks in the concrete, thus blocking effectively further water passage. The active chemical that made up VETOPROOF CM741 catalyzes to reactivate the crystallization process every time water penetrates the structure through newly formed capillaries, therefore, ensuring permanent water tightness.

### Advantages

- Non-toxic and does not contain any momentary organic components.
- Excellent resistance to freeze-thaw cycles.
- It can be applied even on the humid surface.
- Guarantees permanent water sealing of concrete.
- It can be applied to all structurally sound concrete, whether old or new.
- Active components present in the watertight concrete reactivates upon impact with the water.
- Treated concrete is completely watertight after 5 days.
- Highly resistant to deicing salts, sulphuric acid, and hydrochloric acid during at least 35 days.
- Shields concrete and reinforcement from corrosion due to water.

### Standards Compliance

- ASTM D4799
- ASTM E96
- ASTM D4060

### Technical Data

Vetoproof CM741	Typical Values @ 25°C
Pot Life	60 Minutes
Density	1.6 kg/Ltr approx.
Chloride content	Nil
Water Resistance at 5 bar EN12390-8:2009	Pass for positive and negative pressure
Long Term Water Permeability	Nil
Water Absorption	0.0008
Water Vapor Transmission ASTM E96	<25 g/m <sup>2</sup> @ 29 hours
Application temperature	Minimum + 5°C

### Usage Instructions

#### Surface Preparation

All surfaces where Vetoproof CM741 has to be applied must be clean and have an open capillary system. Eliminate laitance, dirt, grease, and other loose materials utilizing high-pressure water jetting or wet sandblasting. Defective concretes such as cracks and honeycombs, etc., have to be chased out and repaired before the application. Also, make sure that all surfaces must be damp but not totally wet before progressing the work.

## Mixing

If the use of masonry brush is the application method, mix 7-7.5 liters of water with 25kg of Vetoproof CM741, while when using a power-spray gun, prepare a mixture of 8 – 8.5 liters of water with 25kg of the product.

Mix only as much product as necessary and ensure to stir the mixture regularly. If the mixture starts to set, it is not advisable to add more water; instead, re-stir the prepared mixture to reinstate its workability.

## Application

Apply Vetoproof CM741 into two coats with the use of a masonry brush or power-spray gun. Make sure to apply the second coat while the first coat is still "green".

Keep all areas where Vetoproof CM741 is applied damp, protected against direct exposure from sunlight, wind, and frost by covering the area with polythene sheeting, damp hessian cloth, etc., for a period of 5-7 days.

Ensure that the period between applying the first and second layer is between 3 – 4 hours at a temperature of 20°C.

## Cleaning

Clean all tools employed to apply Vetoproof CM741 with water before it hardens; otherwise, mechanical means are needed.

## Packaging & Coverage

Product	Pack Size	Yield
Vetoproof CM741	25kg Bags	1.6 kg/m <sup>2</sup> /1mm thickness

Stated consumption data are for general guidance. Actual consumption depends on the nature of substrate, method of application, and wastage.

## Shelf Life & Storage

The original sealed bag of Vetoproof CM741 has a shelf life of 12 months, provided it is stored clear of ground in a dry and shaded place below 35°C.

## Limitations

- Do not apply Vetoproof CM741 on temperatures below 5°C.
- Vetoproof CM741 could not be used as an additive to concrete or plasters.
- Vetoproof CM741 is not suitable for use as curing compounds.

## LEGAL DISCLAIMER

Saveto endeavors to ensure that any advice, recommendations, information it may give is accurate and correct. It cannot accept any liability either directly or indirectly arising from the use of its products because it has no direct or continuous control over where or how its products are applied, whether or not following any advice, specification, recommendation, or information given by us. Saveto has the right to change any of the technical datasheets' specifications upon its discretion without prior notification. Hard copies of TDSs are printed once or twice a year. Our technical data sheets are continuously updated as per R&D improvements and new 3rd party testing; kindly refer to our website for the latest updated TDSs.

## Health & Safety

Vetoproof CM741 contains cement powders that release alkalies that can be harmful to the skin when mixed or become damp. During use, avoid inhalation of dust and contact with skin and eyes. Wear suitable protective clothing, gloves, eye protection, and respiratory protective equipment. The use of barrier creams provides additional skin protection. In case of skin contact, rinse with plenty of clean water, then cleanse with soap and water. In case of contact with the eye, rinse immediately with plenty of clean water and seek medical advice. If swallowed, seek medical attention immediately – do not induce vomiting.

Vetoproof CR747 is non-flammable.

## Additional Information

Saveto manufactures a wide range of construction chemicals and specialty products for various applications divided into the following product groups:

- Waterproofing Systems.
- Concrete Repairs & Grouts.
- Flooring Systems.
- Wall & Facade Systems.
- Sealants and Joints.
- Renders & Finishes.
- Plasters & Masonry.
- Tile adhesives & Grouts.
- Primers & Ancillary Products.
- Thermal Insulation Systems
- Protective Coatings
- Accessories

Saveto also provides various technical information such as CAD details, detailed method statements, specification clauses, application manuals, product selectors and technical support both in contractors and consultants offices as well as construction sites.

For further information on these products and systems kindly check our website or contact your local Saveto representative.