

SEALANTS AND JOINTS



Vetoflex PU788

High performance non-sag, elastomeric single component PU Sealant, for wide joints and overhead application.

Uses

- Primerless sealing pre-cast panel joints and expansion joints.
- As a general elastic adhesive for materials with dissimilar properties and thermal expansion coefficients.
- Movement and static joint sealing in various construction industry requirements.

Product Description

Vetoflex PU788 is one part, moisture curing, water resistant, low modulus elastomeric joint sealant based on polyurethane. It is suitable for movement and connection joints for indoor and outdoor applications. Vetoflex PU788 is a paintable weather-resistant sealant with versatile usage both as a sealant and a general adhesive in the construction industry for various substrates, including concrete, steel, wood, and many others.

Advantages

- Suitable for overhead, vertical and horizontal joints.
- Weather-resistant, suitable for External & Internal applications.
- Easy application using a caulking gun.
- Paintable with non-solvent or water-based paints after curing in static joints (i.e., around door perimeters).
- No crack or craze under UV exposure.
- Non-sag and non-staining.
- It does not require a primer and exhibits tenacious adhesion to most building materials.
- Excellent movement accommodation.

Design Criteria

Vetoflex PU788 use should follow standard concrete joints practices; sealants need either backing rod or joint breaker tapes to prohibit 3 point adhesion and allow movement freedom in the desired design. Saveto recommends the use of ACI 224.3-95 (re-approved 2013) for joint design.

Technical Data

Vetoflex PU788	Typical Values @ 23°C
Density	1.48 Kg/Liter (Grey)
Service Temperature	-50 to 90°C
Elongation at Break ISO8339	> 200%
Tear Resistance - ISO 34	~ 11.7 N/mm
Shore A Hardness	40 @ 28 days
Elastic Modulus @100% ISO8339	0.27 N/mm ²
Movement Accommodation Factor (MAF)	± 25%
Adhesion Bond to Concrete	Higher than host concrete cohesive strength.
Color Availability	White, Grey, Beige as standard, others upon request.
Extrusion Rate ASTM C1183 @ 14 days moist cure	≥ 10ml/min
Curing Rate	~ 2 mm/24 h (23 °C / 50 % RH)

Standards Compliance

- ASTM C920 Type S, Grade NS, Class 25, use T1, NT, A, and M
- ISO 11600, F 25 LM h TT-S-00230C Class A, Type II
- ASTM C1183

Usage Instructions

Joint Design

Standard design dimensions for concrete elements as per DIN 18 540 /table 3:

Joint Distance (m)	2	3	4	6	8
Design Joint Width (mm)	15	20	25	40	50
Minimum Joint Width (mm)	12	17	22	35	45
Joint Depth	8	10	13	20	25

Surface Preparation

Clean all joint surfaces and remove any dust, unsound material, plaster, oil, paint, grease, corrosion deposits, or algae. Roughen the surfaces, remove any laitance and expose aggregate by light scabbling or grit-blasting. Remove oil and grease deposits by steam cleaning, detergent scrubbing, or use a proprietary degreaser. Before positioning a bond breaker, check any expansion joint filler to ensure it is tightly packed with no gaps or voids at the base of the sealing slot. The use of a bond breaker is not required in expansion joints containing cellular polyethylene joint filler, backing rod (Vetoflex PBR). For construction or contraction joints, use a bond breaker tape or back-up strip.

Where a particularly neat finish is required, mask the joint's face edges before sealing and remove immediately after tooling is completed.

Priming

The use of a primer is generally not required when using Vetoflex PU788. However, where it is hard to bond substrates such as PVC or where highly porous substrates are in question, please contact Saveto local office for assistance on suitable primer choice.

Application

Cut and remove the end of the sachet and place the sachet in the Saveto bulk gun. Fit the nozzle and cut at 45 degrees to a suitable size for sealing the joint. Extrude the sealant firmly into the joint. Tool flush within 5 minutes of application to ensure good contact between the sealant and the substrate.

Cleaning

Remove Vetoflex PU788 from tools, equipment, and mixers with Vetonit Solvent XX400 immediately after use. Hardened material can only be removed mechanically.

Legal Disclaimer

Saveto endeavors to ensure that any advice, recommendations, information it may give is accurate and correct. It cannot accept any liability either directly or indirectly arising from the use of its products because it has no direct or continuous control over where or how its products are applied, whether or not following any advice, specification, recommendation, or information given by us. Saveto has the right to change any of the technical datasheets specifications upon its discretion without prior notification.

Hard copies of TDSs are printed once or twice a year. Our technical data sheets are continuously updated as per R&D improvements and new 3rd party testing; kindly refer to our website for the latest updated TDSs.

Packaging & Coverage

Product	Pack Size	
Vetoflex PU788	600 mL Sausages	
Coverage		
Joint Width (mm)	Joint Depth (mm)	Length Filled / Sausage (m)
15	8	5
20	10	3
25	13	1.85
40	20	0.75
50	25	0.5

Stated consumptions data are for general guidance. Actual consumption depends on the nature of substrate, method of application and wastage.

Shelf Life & Storage

The original sealed sausages of Vetoflex PU788 have a shelf life of 12 months, provided it is stored clear of ground in a dry, shaded place below 25°C.

Health & Safety

Vetoflex PU788 is not classified as hazardous. It contains Isocyanate.

For information and advice on the safe handling, storage, and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological, and other safety-related data.

Additional Information

Saveto manufactures a wide range of construction chemicals and specialty products for various applications.

For further information on these products and systems kindly check our website or contact your local Saveto representative.