



Vetonit Putty Fine Extra

High quality water-based wall putty, designed for smooth and level finishes

Uses

- Use for leveling of minor surface undulations.
- Apply internally in dry conditions onto the walls & ceilings.
- Use on concrete, plastered surfaces that are smooth, precast concrete surfaces, and on wood.
- Suitable for use over plastered surfaces with Saveto products, gypsum boards, and wood surfaces.
- Suitable for use over Vetonit Putty WR.

Product Description

Vetonit Putty Fine Extra is a water-based putty with high smooth finish. It is supplied as a wet putty in pre-weighed pails ready to use on-site. Vetonit Putty Fine Extra is a high-quality & performance product that is used as a thin underlayment to repair undulations. It provides a very smooth surface finish that is ideal for subsequent application of paint & decorative coatings. Generally, Vetonit Putty Fine Extra can be applied in maximum thickness of 0.7 mm.

Advantages

- Ready to use and very easy to apply.
- It gives a level & smooth finish by using a putty flat trowel.
- Excellent filling property.
- High adhesion to the substrate.
- Toughness increases with time.
- Very low VOC.
- Sandable.
- Excellent hiding power.
- Friendly smell.

Technical Data

Vetonit Putty Fine Extra	Typical Values @ 25°C
Appearance	Pale creamy
Finish	Matt, smooth finish
Wet Film Thickness (WFT)	200 - 400 micron
Application Temperature	+ 5 °C to + 35 °C
Full Dry Time	3 - 4 Hours
Specific Gravity	1.65 - 1.75
Viscosity	120,000 - 160,000 CPS (Sp#7 @20 rpm)
Solid Content	68 - 74 %
PH	8.00 - 9.00

Standards Compliance

- SASO ASTM C270, Type O
- BS EN 998-2

Usage Instructions

Surface Preparation

The surface should be sound, clean, free from loose material, grease, laitance, dirt curing compound, etc.

For previously painted surfaces, remove the old paint before the application of Vetonit Putty Fine Extra.

Allow wet surfaces to dry completely before the putty application.

Application

Generally, apply Vetonit Putty Fine Extra in single or double coats.

Apply Vetonit Putty Fine Extra to the substrate by pressing the putty firmly. Use a flat trowel to work the mixed material to a smooth level.

Once the first coat dries, apply a second coat as necessary.

After applying Vetonit Putty Fine Extra, it is recommended to apply one coat of alkali-resistant primer followed by two coats of acrylic emulsion paint or other suitable coatings.

Drying

Vetonit Putty Fine Extra is self-drying and does not require water treatment.

Cleaning

Clean all tools immediately after finishing with water. As for the hardened materials, clean them mechanically.

Packaging & Coverage

Product	Pack Size	Coverage
Vetonit Putty Fine Extra	25 Kg Plastic Pail	3 m ² /kg @ 2 coats

Stated consumption data are for general guidance. Actual consumption depends on the nature of the substrate, method of application, and wastage.

Shelf Life & Storage

The original sealed container of Vetonit Putty Fine Extra has a shelf life of 12 months, provided it is stored clear of ground in a dry, shaded place between 5 °C up to 35 °C.

Health & Safety

Avoid Vetonit Putty Fine Extra direct contact with eyes or skin. It is recommended to use protective gloves and goggles during application. Any skin contact should be washed with soap & water. In case of eye irritation, immediately wash with a copious amount of clean cold water. Seek medical advice.

Vetonit Putty Fine Extra is non-flammable.

For further information, please refer to the material safety data sheet.

Additional Information

Saveto manufactures a wide range of construction chemicals and specialty products for various applications.

For further information on these products and systems kindly check our website or contact your local Saveto representative.

Legal Disclaimer

Saveto endeavors to ensure that any advice, recommendations, information it may give is accurate and correct. It cannot accept any liability either directly or indirectly arising from the use of its products because it has no direct or continuous control over where or how its products are applied, whether or not following any advice, specification, recommendation, or information given by us. Saveto has the right to change any of the technical datasheets specifications upon its discretion without prior notification.

Hard copies of TDSs are printed once or twice a year. Our technical data sheets are continuously updated as per R&D improvements and new 3rd party testing; kindly refer to our website for the latest updated TDSs.