



Vetotouch Textura

Cementitious polymer modified decorative finish coat applied at thicknesses from 5 to 20mm

Uses

- External and internal building facades.
- On block walls and concrete surfaces.
- On scratch coated overhead surfaces.

Product Description

Vetotouch Textura is a polymer-modified cement-based render coat composed of hydraulic binders, selected aggregates, special pigments, and high-performance additives. It is supplied as a dry powder in pre-weighted bags ready to use on-site, which requires only the addition of clean water to produce cohesive mortar. Vetotouch Textura is a high-quality product and is suitable for external applications. Vetotouch Textura is available in white, Saveto standard colors, and custom colors with minimum order restrictions.

Advantages

- Factory controlled pre-blend ensures consistently high quality.
- Requires only the addition of water on-site at the time of usage.
- Uniform color / mass.
- Improved workability and curing.
- Easy application with uniform work flow enables high productivity and superior finishing.
- Strong adhesion on a variety of substrates.
- Internal and external applications.
- Weather-resistant.
- UV stable pigment provides resistance to fading and eliminates the need for additional paint.
- Suitable for humid and dry conditions.

Technical Data

Vetotouch Textura	Typical Values @ 25°C
Appearance	Colored Powder
Wet Density	1.9 Kg/Liter
Pot Life	60 minutes
Compressive Strength BSEN 1015-11	> 12 N/mm ² @ 28 Days
Flexural Strength BSEN 1015-11	> 2 N/mm ² @ 28 Days
Bond Strength to concrete BSEN 1015 - 12	> 0.4 N/mm ² @ 28 Days
Thermal Conductivity Coefficient - EN1745, A12	0.9 W/ mK

Standards Compliance

- BSEN 998 - 1 : CR, CS IV, Wc1
- ASTM C926
- BSEN 13914

Usage Instructions

Surface Preparation

The substrate should be sound, clean, free from loose material, grease, laitance, dirt curing compound, etc.

Before the Vetotouch Textura application, wet the entire surfaces with clean potable water. The surface should look damp at the time of the Vetotouch Textura application.

Mixing

For manual application, add to the mixing container 8-10 liters of water for each 50kg bag of Vetotouch Textura or 12 liters / 50kg bag for machine application. Add the powder to the water and mix with a mechanical plaster mixer or low-speed electric drill fitted with a suitable paddle for 3-4 minutes until achieving a uniform, lump-free consistency.

Leave the mixed material to stand for 10min and briefly remix without adding water.

For small batch quantities, mix the material manually for approx. 1-2 min or when achieving a homogeneous mix.

Smooth Concrete Surface

Prepare the surface by using a suitable mechanical key Spatter Dash product range from Saveto. Add 1.5 to 2.0 liter of Vetobond AB432 to the mixing water and adjust the water requirement accordingly for each 50kg bag. Follow the same mixing procedure as described above.

Use the mixed material within 1 hour.

Do not add water once the mixed mortar starts to harden.

Application

Apply Vetotouch Textura on smooth surfaces in a single or two coats by trowel application to achieve the desired thickness of 5-20mm.

Apply the mixed material using the hawk and trowel technique. Rod or screed to uniform thickness, not exceeding 20mm for a single coat or 10mm per coat for multiple layers. Press the first layer tight against the surface.

For the second layer, allow the plaster to partially set (60-120 min depending on weather). Apply the second layer as described above.

If the second layer is carried out the next day, spray water the surface.

Legal Disclaimer

Saveto endeavors to ensure that any advice, recommendations, information it may give is accurate and correct. It cannot accept any liability either directly or indirectly arising from the use of its products because it has no direct or continuous control over where or how its products are applied, whether or not following any advice, specification, recommendation, or information given by us. Saveto has the right to change any of the technical datasheets specifications upon its discretion without prior notification.

Hard copies of TDSs are printed once or twice a year. Our technical data sheets are continuously updated as per R&D improvements and new 3rd party testing; kindly refer to our website for the latest updated TDSs.

Curing

It is vital to cure Vetotouch Textura surface with clean potable water 2 times a day for 3 days. During hot and dry conditions, extend curing period for a minimum of 5-7 days. It will help to obtain high physical properties.

To protect the final color look, it is recommended to apply one coat of Saveto Vetoseal product range (contact the technical department for advice).

Cleaning

Clean all tools employed to apply Vetotouch Textura with water before it hardens; otherwise, mechanical means are needed.

Packaging & Coverage

Product	Pack Size	Yield
Vetotouch Textura	50kg Bag	34 Liters

Stated consumption data are for general guidance. Actual consumption depends on the nature of substrate, consistency used, method of application, and wastage.

Shelf Life & Storage

The original sealed bag of Vetotouch Textura has a shelf life of 12 months, provided it is stored clear of ground in a dry, shaded place below 35°C.

Health & Safety

Vetotouch Vetotouch Textura is highly alkaline; therefore, avoid direct contact with eyes or skin. It is recommended to use protective gloves and goggles during application. Any skin contact should be wash with soap & water. In case of eye irritation, immediately wash with a copious amount of clean cold water. Seek medical advice.

Vetotouch Textura is non-flammable. For further information, please refer to the product material safety data sheet.

Additional Information

Saveto manufactures a wide range of construction chemicals and specialty products for various applications.

For further information on these products and systems kindly check our website or contact your local Saveto representative.