



Vetoproof UM870

Pure PU high performance single-component high viscous cold liquid applied waterproofing membrane

Uses

- Wet areas: kitchens, bathrooms, swimming pools, etc.
- Basements, tunnels, subways, and culverts. inverted roofs, suspended slabs, balconies.
- Tanking systems, flooring with pedestrian traffic.
- Suitable for surface with stagnant water, roofs, terrace, flowerbeds, roof with polyurethane insulation foam.
- Use for internal and external areas.

Product Description

Vetoproof UM870 is a premium quality single-component high viscous polyurethane waterproofing membrane; the product is a cold liquid applied that cures by reaction with atmospheric moisture to form a highly elastic rubbery jointless waterproofing membrane.

Advantages

- Easy to apply with brush, roller, or airless spray.
- A jointless application that is easy to detail.
- Crack bridging highly elastic membrane at various temperatures.
- Non-staining and pitch free formulation.
- Outstanding barrier properties ensure protection against corrosive soil conditions.
- Easy to repair and maintain.
- Fully bonded, prohibiting lateral migration of water.
- Thermally and chemically stable, resistant to oxidation and embrittlement.
- Excellent adhesion to wide range of construction materials.

Standards Compliance

- ASTM C836

Technical Data

Vetoproof UM870	Typical Values @ 25°C, 50% RH
Color	Black, white, gray
Tack Free Time (Hours)	3
Specific Gravity	1.45 ± 0.2
Skin Over Time (Minutes)	90
Solid Content (by weight %)	95
Permeability ASTM E96	0.035
Water Vapor Transmission ASTM E96 (gm/m ² /24 hrs.)	9.6
Elongation (%) ASTM D412	> 400
Tensile Strength (MPa) ASTM D412	2.00
Application Temperature (°C)	5 to 40
Adhesion in peel (N) (Concrete) ASTM C794	92.3
Shore A Hardness: ASTM D2240	> 45
VOC Content (gm/liter)	< 150
Service Temperature (°C)	-20 to 80
Re-coat interval (Hours)	4

Usage Instructions

Surface Preparation

All surfaces to be applied with Vetoproof UM870 must be clean and have an open capillary system. Eliminate laitance, dirt, grease, and other loose materials using high-pressure water jetting or wet sandblasting. Defective concretes such as cracks and honeycombs have to be chased out and repaired before the application.

Priming

Priming is not usually required on good quality concrete substrates; however, for highly porous or absorbent concrete, use Vetoseal XX777-50. Or mix 1 part of Vetonit Solvent XX400 with 3 parts of Vetoproof UM870 and use as primer.

Application

Apply Vetoproof UM870 by a brush, roller, or an airless spray gun. Use glass fiber scrim and joint tapes on corners and critical areas for membrane reinforcement. Tiling over Vetoproof UM870 is possible; in such cases, spray sharp sand over Vetoproof UM870 while still wet, 24 hours later, remove all excess sand, and use a suitable tile adhesive from Saveto Tiling Systems Product Range to bond the tiles directly over the membrane.

Curing

Allow Vetoproof UM870 to cure for a minimum of 24 hours before placing the protection. Protect the membrane with a cementitious screed or protection boards where damage to the membrane is possible.

Cleaning

Clean all tools employed to apply Vetoproof UM870 with Vetonit Solvent XX400 before it hardens; otherwise, mechanical means are needed.

Legal Disclaimer

Saveto endeavors to ensure that any advice, recommendations, information it may give is accurate and correct. It cannot accept any liability either directly or indirectly arising from the use of its products because it has no direct or continuous control over where or how its products are applied, whether or not following any advice, specification, recommendation, or information given by us. Saveto has the right to change any of the technical datasheets specifications upon its discretion without prior notification.

Hard copies of TDSs are printed once or twice a year. Our technical data sheets are continuously updated as per R&D improvements and new 3rd party testing; kindly refer to our website for the latest updated TDSs.

Packaging & Coverage

Product	Pack Size	Theoretical Coverage
Vetoproof UM870	15 Liter Pail	0.95 m ² /liter @ 1 mm thickness Note: Maximum thickness per coat is 750 microns

Stated consumption data are for general guidance. Actual consumption depends on the nature of the substrate, method of application, and wastage.

Shelf Life & Storage

The original sealed pail of Vetoproof UM870 has a shelf life of 12 months, provided it is stored clear of ground in a dry and shaded place below 35°C.

Health & Safety

Wear suitable protective clothing, gloves, and eye protection. If working in confined areas, suitable respiratory protective equipment must be used. The use of barrier creams provides additional skin protection. In case of contact with skin, rinse with plenty of clean water, then cleanse with soap and water. Do not use solvent. In case of contact with the eyes, rinse immediately with plenty of clean water and seek medical advice. If swallowed, seek medical attention immediately - Do not induce vomiting.

Vetoproof UM870 is flammable, do not use near to open flames.

Refer to product MSDS for further information.

Additional Information

Saveto manufactures a wide range of construction chemicals and specialty products for various applications.

For further information on these products and systems kindly check our website or contact your local Saveto representative.