


PLASTERS AND MASONRY



Vetonit Masonry Mortar MMR510

Premixed Cementitious Masonry Mortar for Concrete Masonry Blocks

Uses

- Masonry mortar for installing (CMU) Concrete Masonry Units (solid, hollow, insulated)
- Use Masonry Mortar for filling walls and joints.

Product Description

vetonit Masonry Mortar MMR510 is a cement-based premixed mortar composed of hydraulic binders, selected aggregates, and high-performance additives. It is supplied as a dry powder in pre-weighed bags ready to use on-site, which requires only the addition of clean water to produce cohesive mortar. Masonry Mortar is a premium quality product that contains a special adhesion additive. Masonry Mortar can be applied in thickness from 8 mm to 20 mm.

Vetonit Masonry Mortar MMR510 complies with ASTM C-270, and it is available as Type N, S or M.

Advantages

- Factory controlled pre-blend ensures consistently high quality..
- Requires only the addition of water on-site at the time of usage.
- Suitable for ME harsh weather conditions.
- Strong adhesion on a variety of concrete blocks.
- Strong bond in blocks & wall joints.
- Internal & external applications.
- Suitable for wet to dry areas.
- Free from Asbestos, complies with Green Building Regulations.

Technical Data

| Vetonit Masonry Mortar | Typical Values @ 25°C | |
|------------------------------|-----------------------|--|
| Appearance | Grey colour Powder | |
| Aggregate size | max 2.4 mm. | |
| Wet density (Kg/Liter) | ~ 1.90 | |
| Setting Time @ 25°C | 3 - 4 hrs | |
| Compressive Strength, Type N | > 6 | |
| @ 28 day (MPa) | | |
| Compressive Strength, Type S | > 12.4 | |
| @ 28 day (MPa) | × 12.4 | |
| Compressive Strength, Type M | > 17.5 | |
| @ 28 day (MPa) | | |
| Air Content | < 12 % | |
| Water Retention | > 75 % | |
| Reaction to Fire | Class A1 | |
| (BS EN 998-2) | | |

Standards Compliance

- ASTM C270, Type N, S and M
- BS EN 998-2



PLASTERS AND MASONRY

Usage Instructions

Block Surface Preparation

The block wall surface should be sound, clean, free from loose material, grease, laitance, dirt curing compound, etc.

Before Masonry Mortar's application, wet the entire surface with clean potable water, and the surface should look damp at the time of Masonry Mortar's application.

It is recommended to apply a DPC membrane on the ground before laying the first row of blocks (solid blocks).

Mixing

Add to the mixing container 6.5 - 8.5 liters of water for each 50Kg bag of Masonry Mortar. Add the powder to the water and mix with a mechanical plaster mixer or low-speed electric drill fitted with a suitable paddle until achieving a uniform, lump-free consistency.

Leave the mixed material to stand for 10 min and briefly remix without the addition of water.

Blend Masonry Mortar manually for small quantities and maintain the correct amount of powder to water. Mix for approximately 1-2 minutes, until achieving a homogeneous mix.

Application

Neutralize the suction of the block surface with water before applying mortar. Remove any excess water.

Spread Masonry mortar with a trowel on the surface and joints where the blocks are mounted.

Fill joint in a similar way as conventional sand/cement mortar.

After stiffening, give the masonry mortar a final smoothing to remove protrusions and eliminates undulations.

Cleaning

Clean all tools immediately after finishing by water. Clean hardened material mechanically.

Packaging & Coverage

| Product | Pack Size | Consumption |
|--|---|-----------------------|
| Masonry Mortar | 50kg Bag | \approx 30 Lit wet/ |
| | | 50kg bag |
| Product | Coverage | |
| | 15 L.M/ 10mm (Solid block 400x200x200 mm | |
| Masonry Mortar 22 L.M/ 10mm (Solid blo 400x200x150 mm | | |
| | 31 L.M/ 10mm (Solid block 400x200x100 mm | |

Stated consumption data are for general guidance. Actual consumption depends on the nature of the substrate, method of application, and wastage.

Shelf Life & Storage

The original sealed bag of Masonry Mortar has a shelf life of 12 months, provided it is stored clear of ground in a dry, shaded place, at temperatures between 5°C - 35°C.

Health & Safety

Masonry Mortar is highly alkaline; therefore, avoid direct contact with eyes or skin. It is recommended to use protective gloves and goggles during application. Any skin contact should be wash with soap & water. In case of eye irritation, immediately wash with a copious amount of clean cold water. Seek medical advice.

Masonry Mortar is non-flammable.

For further information, please refer to the material safety data sheet.

Additional Information

Saveto manufactures a wide range of construction chemicals and specialty products for various applications.

For further information on these products and systems kindly check our website or contact your local Saveto representative.

Legal Disclaimer

Saveto endeavors to ensure that any advice, recommendations, information it may give is accurate and correct. It cannot accept any liability either directly or indirectly arising from the use of its products because it has no direct or continuous control over where or how its products are applied, whether or not following any advice, specification, recommendation, or information given by us. Saveto has the right to change any of the technical data sheets specifications upon its discretion without prior notification.

Hard copies of TDSs are printed once or twice a year. Our technical data sheets are continuously updated as per R&D improvements and new 3rd party testing; kindly refer to our website for the latest updated TDSs.