



Vetotouch Europa

Cementitious polymer modified decorative finish coat applied at thicknesses from 1 to 5mm

Uses

- External and internal building facades.
- As a finish coat for EIFS / ETICS systems.
- Decorative Finish on Plastered and Concrete Walls and Precast.
- Renovating Building Facades
- Decorative European effects: Mexican, Spanish, Antique, and Textured.
- As a Low maintenance Decorative coat

Product Description

Vetotouch Europa is a cement-based decorative finish composed of hydraulic binders, selected aggregates, and special additives. It is supplied as a dry powder in pre-weighed bags ready to use on-site, which requires only the addition of clean water to produce easily workable mortar.

Advantages

- Water and Weather Resistant
- Fire Resistant
- Breathable, Improves Indoor Air Quality
- Low maintenance and Economical
- Dampness tolerant, No peeling.
- Internal and External use
- Suitable for Dry and Wet conditions
- Free from Asbestos, complies with Green Building Regulations

Technical Data

Vetotouch Europa	Typical Values @ 25°C
Appearance	Colored Powder
Wet Density (Kg/Liter)	1.5
Pot Life (Hours)	2 approx
Compressive Strength BSEN 1015-11 @ 28 Days (N/mm ²)	> 7
Flexural Strength BSEN 1015-11 @ 28 Days (N/mm ²)	> 2
Bond Strength to concrete BSEN 1015 - 12 @ 28 Days (N/mm ²)	> 0.5
Thermal Conductivity - K value	0.5 W/ mK
VOC (gm/liter)	< 10

Standards Compliance

- BS EN998-1 : CSIV, Wc1

Usage Instructions

Surface Preparation

Compatible surfaces: Plastered walls, ceilings, concrete walls, cement and gypsum boards, precast, EIFS/ETICS.

The substrate should be sound, clean, free from loose material, grease, laitance, dirt curing compound, etc.

Before the application, wet the entire surfaces with clean potable water.

Mixing

Add to the mixing container 7.5 - 8.5 liters of water for each 25kg bag (15 - 17 liters for each 50 kg bag) of Vetotouch Europa. Add the powder to the water and mix with a mechanical plaster mixer or low-speed heavy-duty electric drill fitted with a suitable paddle until achieving a uniform, lump-free consistency. Leave the mixed material to stand for 10min and briefly remix without adding water.

For small batch quantities, mix the material manually for approx. 1 - 2 min or when achieving homogeneous mix.

A manual application is considered (not by spray machines), optionally, adding 0.5 and 1.0 liter of Vetobond AB432 to the mixing water and adjusting the water requirement accordingly for each 25kg and 50 kg bag. Follow the same mixing procedure as described above.

Use the mixed material within 60 - 120 minutes. Do not add water once the mixed mortar starts to harden.

Application

Apply Vetotouch Europa in a single or multiple coats on the prepared surfaces by trowel application (or by spray, roller) to achieve the desired thickness of 1-5mm.

Curing

It is vital to cure Vetotouch Europa surface with clean potable water 2 times a day for 3 days. During hot and dry conditions, extend the curing period for a minimum of 5-7 days. It will help to obtain high physical properties. An acrylic-based curing compound can be used.

To protect the final color look, it is recommended to apply one coat of Vetoseal product range (contact the technical department for advice).

Legal Disclaimer

Saveto endeavors to ensure that any advice, recommendations, information it may give is accurate and correct. It cannot accept any liability either directly or indirectly arising from the use of its products because it has no direct or continuous control over where or how its products are applied, whether or not following any advice, specification, recommendation, or information given by us. Saveto has the right to change any of the technical data sheets specifications upon its discretion without prior notification.

Hard copies of TDSs are printed once or twice a year. Our technical data sheets are continuously updated as per R&D improvements and new 3rd party testing; kindly refer to our website for the latest updated TDSs.

Cleaning

Clean tools with water before the mortar hardens. After the hardening, remove its residuals mechanically only.

Packaging & Coverage

Product	Pack Size	Consumption
Vetotouch Europa	25 kg Bag	~ 1.8 kg/m ² /1mm.
	50 kg Bag	

Stated consumption data are for general guidance. Actual consumption depends on the nature of substrate, consistency used, method of application, and wastage.

Shelf Life & Storage

The original sealed bag of Vetotouch Europa has a shelf life of 12 months, provided it is stored clear of ground in a dry, shaded place below 35°C.

Health & Safety

Vetotouch Europa is highly alkaline; therefore, avoid direct contact with eyes or skin. It is recommended to use protective gloves and goggles during application. Any skin contact should be wash with soap & water. In case of eye irritation, immediately wash with a copious amount of clean cold water. Seek medical advice. Vetotouch Europa is non-flammable.

For further information, please refer to the product material safety data sheet.

Additional Information

Saveto manufactures a wide range of construction chemicals and specialty products for various applications.

For further information on these products and systems kindly check our website or contact your local Saveto representative.