



Vetonit Gypsum Joint Compound

Premium premixed compound for gypsum board joints

Uses

- It can be used to level minor surface undulations.
- It can be used internally on horizontal and vertical surfaces.
- It can be used as a smooth compound for jointing and as a finish on gypsum plasterboard joints.
- Suitable for dry to normal humidity.

Product Description

Gypsum Joint Compound is composed of Portland cement, fine fillers, bonding chemicals, and high-performance additives. It is supplied as a dry powder in pre-weighed bags ready to use on-site, and only requires the addition of clean water to produce a cohesive mix. Gypsum Joint Compound is ideal for levelling, finishing, and filling gypsum board joints. Gypsum Joint Compound can be generally applied in layers that are 1 to 5 mm thick.

Advantages

- Factory-controlled pre-blend ensures consistently high quality.
- It is ready to use on site and only requires the addition of water.
- It is suitable for internal applications.
- It is easy to apply, with superior finishing achieved with minimum effort.
- Strong adhesion to the substrate.
- It is a crack-free compound when it cures.
- It achieves a very smooth finish.
- It is specially designed to complement gypsum board installations.

Technical Data

Gypsum Joint Compound	Typical Values @ 25°C
Appearance	White Powder
Aggregate Size (mm)	0.15 max
Wet Density (kg /liter)	1.5
Application Thickness (mm)	Joint Width: 1 - 5 Levelling: 1 - 3
Pot Life (Hours)	3
Compressive Strength EN 1018 - 11 (N/mm ²)	5.5
Flexural Strength EN1 015-11 (N/mm ²)	1.0
Adhesion @ day 28 (N/mm ²)	0.45

Standards Compliance

- BS EN 998-1

Usage Instructions

Surface Preparation

The surface should be sound, clean, and free from loose material, grease, laitance, dirt-curing compounds, etc.

Mixing

For mechanical mixing, add 7.5 - 8.8 litres of water to the mixing container for each 20kg bag of Gypsum Joint Compound. Mix using an automatic plaster mixer or a low-speed electric drill fitted with a suitable paddle until a uniform, lump-free consistency is achieved.

Allow the mixture to stand for about 10 minutes, then remix briefly without adding more water.

Mix small batch quantities manually for approx. 1 - 2 min, or until a homogeneous mix is achieved.

When required, add 0.5 litres of Vetobond AB432 to the mixing water and adjust the water requirement for each 20kg bag accordingly. Follow the same mixing procedure.

Use the material within 2 - 3 hours. Do not add water once the mixed filler mortar begins to stiffen or harden.

Application

Generally, apply Gypsum Joint Compound in a single coat. Spread the Gypsum Joint Compound to the area with a wide spatula while filling and pressing firmly into the joints.

Place joint tape over the joints with a small spatula, spread the excess compound over the joint tape, and level it smoothly to the surface while edging out to the sides. After hardening, smooth rub the joints to the desired finish.

Apply Gypsum Joint Compound manually as a skim coat on top of the gypsum board to achieve a uniform soft surface layer.

Curing

Gypsum Joint Compound sets and cures on its own at room temperature.

Cleaning

Clean all tools with water immediately after finishing. Clean hardened materials mechanically.

Legal Disclaimer

Saveto endeavors to ensure that any advice, recommendations, information it may give is accurate and correct. It cannot accept any liability either directly or indirectly arising from the use of its products because it has no direct or continuous control over where or how its products are applied, whether or not following any advice, specification, recommendation, or information given by us. Saveto has the right to change any of the technical datasheets specifications upon its discretion without prior notification.

Hard copies of TDSs are printed once or twice a year. Our technical data sheets are continuously updated as per R&D improvements and new 3rd party testing; kindly refer to our website for the latest updated TDSs.

Packaging & Coverage

Product	Pack Size	Consumption
Vetonit Gypsum Joint Compound	20 KG Bag	1.1 Kg/m ² /mm Approx.

Stated consumption data are for general guidance. Actual consumption depends on the nature of the substrate, method of application, and wastage.

Shelf Life & Storage

The original sealed container of Vetonit Gypsum Joint Compound has a shelf life of 12 months, provided it is stored off the ground in a dry, shaded place at a temperature below 35°C.

Health & Safety

Gypsum Joint Compound is highly alkaline; therefore, avoid direct contact with your eyes or skin. It is recommended to use protective gloves and goggles during application. Wash any skin contact with soap and water. In case of eye irritation, immediately wash with a copious amount of clean, cold water and seek medical advice.

Gypsum Joint Compound is non-flammable.

For more information, see the material safety data sheet.

Additional Information

Saveto manufactures a wide range of construction chemicals and specialty products for various applications.

For further information on these products and systems kindly check our website or contact your local Saveto representative.